

magnesium oxide caustic

CONTACT US / CONTATTI

Technical Support / Supporto Tecnico
technical@blutec.info

Orders – Enquiries / Ordini – Richieste di Offerta
blutec@blutec.info

Ph. +39 010 25 18 563

Quality: Magnesium Oxide Caustic High Reactivity Size 76 Micron

CHEMICAL COMPOSITION			TYPICAL VALUE	UNIT OF MEASURE	NORMA UNI EN ISO	GUARANTEED VALUE
Magnesium Oxide	MgO	Ignited basis	99,00	% m/m	10058-3:2009	Min 97
Calcium Oxide	CaO		1,48	% m/m	10058-3:2009	Max 1,98
Iron Oxide	Fe ₂ O ₃		0,01	% m/m	10058-3:2009	Max 0,20
Aluminium Oxide	Al ₂ O ₃		0,12	% m/m	10058-3:2009	Max 0,20
Silica Oxide	SiO ₂		0,25	% m/m	10058-3:2009	Max 1,5
Sulfur Oxide	SiO ₃		0,3	% m/m	10058-3:2009	
LOI			2,50	% m/m	26845:2008	Max 3,80-
Surface Area BET			35-55	m ² /gr	26845:2008	-
Reactivity in Citric Acid	Al		20-30	Sec.	Internal method	
Density			750-780	gr/l	UNI EN	
Sizes			98% inf 76 µm		LASER	
Color			White			

INFORMATION

The information herein is given in good faith and believed to be correct as to the best of our knowledge.

The guaranteed values, as sale specifications, are referred to the accurately stored product.

However no representation of warranty, either expressed or implied, is made, in case of different analytical methods. No liabilities are undertaken of the end use results, neither of the unsuitable usage, storage or handling of the product.

PACKAGING

Non returnable

- 25 Kgs bags

- 500kg or 1 Mt big bags.